



DTT-H15

特性 Characteristics	单位 Unit	测试条件 Test conditions		DTT-H15
初始磁导率 μ_i Initial permeability	-	10kHz 0.1mT	25°C	15000 \pm 25%
相对损耗因数 $\tan \delta / \mu_i$ Relative loss factor	$\times 10^{-6}$	100kHz	25°C	< 7
饱和磁通密度 B_s^* Saturation flux density	mT	H=1194A/m	25°C	380
剩磁 B_r^* Remanent flux density	mT		100°C	230
			25°C	100
矫顽力 H_c^* Coercive force	A/m		100°C	75
			25°C	4.4
			100°C	4
相对温度系数 α_{μ_i} Relative temperature	$\times 10^{-6}/^\circ\text{C}$	20°C ~ 60°C		-0.5~2
减落因子 D_f Disaccommodation	$\times 10^{-6}$	1 to 10 minutes		< 2
居里温度 T_c Curie temperature	°C			\geq 115
电阻率 ρ^* Resistivity	$\Omega \cdot \text{m}$			0.1
密度 D^* Density	g/cm^3			4.9

*: 典型值 Average value

